

**SALES & SERVICE
IN YOUR STATE
PH: 1300 658 007**



Megasealed™

Megasealed Bathrooms Aust. Pty Ltd ABN: 84 074 726 757
Megasealed Insulation Aust. Pty Ltd ABN: 84 138 909 985

MEGAFLEX SPECIFICATIONS

ANTI – FUNGUS SILICONE

Quality Characteristics	Unit	Specification	Test Method
1. * Appearance (Characteristic)	-	Paste	Visual
2. * Appearance (Colour)	-	Clear, White, etc.	Visual
3. * Tack Free Time at 23 °C	Minute	15 maximum	JIS A 1439
4.* Slump at 23 °C	mm	3 maximum	JIS A 1439
5.* Extrusion Rate at 23 °C	g	30-80	§ I
6. * Hardness; Type A	-	15-30	JIS K 6249
7. * Tensile Strength	MPa	1.0 minimum	JIS K 6249
8. * Elongation at break	%	400 minimum	JIS K 6249
9.* Tensile Shearing Adhesive Strength (aluminium / aluminium)	MPa	0.5 minimum	JIS K 6249
10.* Designation Failure (%CF)	%	80-100	JIS K 6249

Curing Condition: 23 ± 2 °C, Humidity 50 ± 5 % - 7 days

VT 07/11

megasealed.com.au

**NEW SOUTH WALES
Sydney Head Office**
Unit 5, 133 Beauchamp Road
Postal: PO Box 195
Matraville NSW 2036
Tel: 1300 658 007
Fax: 02 9289 3655
nsw@megasealed.com.au

**ACT
Canberra**
Unit 3, 94 Bayldon Road
Queanbeyan NSW 2620
Tel: 1300 658 007
Fax: 02 6262 6100
act@megasealed.com.au

**QUEENSLAND
Brisbane**
Unit 1, 37 Mortimer Road
Acacia Ridge QLD 4110
Tel: 1300 658 007
Fax: 07 3216 6526
qld@megasealed.com.au

**SOUTH AUSTRALIA
Adelaide**
3/900 South Road
Edwardstown SA 5039
Tel: 1300 658 007
Fax: 08 8371 3500
sa@megasealed.com.au

**VICTORIA
Melbourne**
346 Darebin Road
Fairfield VIC 3078
Tel: 03 9499 1766
Fax: 03 9499 3977
vic@megasealed.com.au

**WESTERN AUSTRALIA
Perth**
2/71 Truganina Road
Malaga WA 6090
Tel: 1300 658 007
Fax: 08 9248 2700
wa@megasealed.com.au